



Neutrasit® Precoat/primer

PRODUCT PROFILE

As suction-control pre-coat to strong, clean, dry basecoats prior to application of thin-coat rubbed or floated renders/renders such as RP240, SP260, ROLLS, NOBLO, conni, KATI or addi.

As priming coat to high- or variable-suction backgrounds, e.g. aerated concrete, Poroton blockwork or perforated masonry units, to reduce absorbency and prevent moisture migration from mortar group P I or P II basecoats.

- aqueous emulsion
- for indoors and outdoors
- milky white while wet
- dries to transparent coating

TECHNICAL DATA

(DIN 53217)

| | |
|------------|-------------------------|
| Density: | 1.05 kg/dm ³ |
| Viscosity: | low |

| | Bucket | Coverage kg/m ² | Coverage m ² /bucket |
|---------------------------|--------------|-------------------------------|------------------------------------|
| Neutrasit® | 5 kg | | |
| Priming coat, diluted 1:1 | | 0.10 | 50 |
| Precoat, undiluted | | 0.18 | 28 |
| Neutrasit® | 15 kg | | |
| Priming coat, diluted 1:1 | | 0.10 | 150 |
| Precoat, undiluted | | 0.18 | 83 |

The above figures are approximate values and may vary according to background type.

PREPARATION

Cover or watertightly mask dirt-sensitive elements, particularly glazing. Protect weather-exposed work surfaces from rain. Clean down existing strong, unpainted basecoats, dust down new renderwork, clean/dust down masonry.

APPLICATION

Precoat: Stir bucket contents well and roll or brush on undiluted material over mortar group P I, P II and P III basecoats, such as LUP222, elfer, UP210 etc. Dilute 1:1 for application to reinforcing mortar, such as SM700, Lustro etc.

Apply Neutrasit uniformly and crosswise to avoid streaking. Thin-coat rubbed or floated renders/renders such as RP240, SP260, ROLLS, NOBLO, conni, KATI or addi may be applied after 24 hours drying time.

Priming coat: Stir bucket contents well and dilute 1:1 with clean water in clean container. Uniformly apply to high-suction masonry, e.g. aerated concrete, Poroton blockwork or perforated masonry units etc., with roller/brush or spray over whole surface using suitable equipment. Allow min. 24 hours drying time prior to application of mortar group P I and P II basecoats, such as LUP222, UP210 etc. Wash tools and equipment with water immediately after use.

PLEASE NOTE

Basecoats shall be fully dried and set. Masonry shall be dry and strong. Do not apply at air and/or wall temperatures below +5°C. Use only clean water to dilute.
Perform preliminary site tests prior to application to other manufacturers' basecoat products.

SAFETY AT WORK

Avoid contact with skin and eyes. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. Professional applicators may obtain a safety data sheet upon request. Once set, the material poses no physiological or ecological hazards.

DISPOSAL

Allow any remaining material to dry. It may then be disposed of, together with container, as domestic or construction site waste.

Liquid product residue is classed under waste code EWC 08 01 12 (waste paint and varnish other than those mentioned in 08 01 11).

Dry product residue is classed under waste code EWC 17 09 04 (mixed construction and demolition wastes other than those mentioned in 17 09 01, 17 09 02 and 17 09 03).

Gisbau code (German hazardous substances classification): M-DF 02

Regional regulations shall be observed.

COMPOSITION

Binder:

Plasticizer-free synthetic resin dispersion

Aggregate:

Special filler mix

QUALITY

The product is subject to continuous quality monitoring.

DELIVERY FORM/SHELF LIFE

5 kg and 15 kg PE bucket.

Shelf life 12 months, subject to cool, frost-free storage (+5°C to +25°C) in original container.

SUPPLY

Via Marmorit approved applicators or local distributors

NOTE

This data sheet, which replaces all previous editions, is designed to provide you with advice and assistance. The information presented herein reflects our present state of knowledge. It cannot, however, embody the sum total of good practice, nor incorporate the provisions of all relevant standards, codes of practice and guidelines. These – together with the relevant application rules and guidelines – shall be duly observed by the applicator!

TECHNICAL ADVICE

Information and advice may be provided by our external representatives or the MARMORIT Technical Department

Marmorit UK GmbH Address - 1 Portview Road, Avonmouth, Bristol – Telephone 0117 982 1042